Type K extension bare Wire

TYPE KCA (Cu vs Cu40) is used for making cable which can be extension for type K thermocouple. The cost is cheaper a lot than Kx type.

1. Chemical Composition

Material	Chemical composition (%)				
	Ni	Fe	Si	Cu	Al
KPCB				100	
KNCB	40			60	

2. Physical properties and Mechnical properties

Material	Density(g/cm3)	Melting point(℃)	Tensile Strength(Mpa)	Volume resistivity (μΩ.cm)	Elongation rate (%)
KPCB	8.9	1450	>190	<1.8(20℃)	>30
KNCB	8.9	1450	>390	<50(20℃)	>25

3. EMF Value range at different temperature

Material	EMF value Vs Pt(μ V)					
	1st tolerance			2nd tolerance		
	100℃	200℃		100℃	200℃	
KPCB	4052-4140	8094-8182		4008-4184	8050-8226	
KNCB						

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy