Ualloy-4J42 (Expansion alloy)

Common Name: 42H Glass Sealing 42, Nilo42, N42, FeNi42

4J42 alloy is mainly composed of iron, nickel elements. It is characterized with a fixed coefficient of expansion. Increase the thermal expansion coefficient and the Curie point with increase of nickel content.

4J42 alloy is widely used the structure of the sealing material in the electric vacuum industry.

Normal composition%

Ni	41.5~42.5	Fe	Bal.	Co	-	Si	≤0.3
Mo	-	Cu	-	Cr	-	Mn	≤0.8
C	≤0.05	P	≤0.02	S	≤0.02	Al	≤0.1

Typical Physical properties

Density (g/cm^3)	8.12
Electrical resistivity at 20℃(Ωmm^2/m)	0.61
Thermal conductivity, λ/ W/(m*℃)	14.6
Curie point T_c/ ℃	360
Elastic Modulus, E/ Gpa	147

Coefficient of expansion

θ/℃	$\alpha_1/10^{-6}℃^{-1}$	θ/℃	$\alpha_1/10^{-6}℃^{-1}$
20~100	5.6	20~400	5.9
20~200	4.9	20~450	6.9
20~300	4.8	20~500	7.8
20~350	4.95	20~600	9.2

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy

Typical Mechanical properties

Tensile Strength	Elongation
Mpa	%
490	35

The heat treatment process	
Annealing	Heated to 900 ±20℃ in a hydrogen atmosphere
Holding time, h	1 hour
cooling	With speed not more than 5 ℃ / min. cooling to below 200 ℃

Style of supply

Alloys Name	Type	Dimension	
Ualloy-4J42	Wire	D= 0.1~8mm	
Ualloy-4J42	Strip	W= 5~250mm	T= 0.1mm
Ualloy-4J42	Foil	W= 10~100mm	T= 0.01~0.1
Ualloy-4J42	Bar	Dia= 8~100mm	L= 50~1000

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy