Ualloy104B (Ni30Cr20)

Common Name: Nikrothal 30, N3, HAI-NiCr 30, Resistohm 30,30-20 Ni-Cr,Nikrothal 3.

Ualloy104B is a nickel-chromium alloy (NiCr alloy) characterized by High resistivity, good oxidation resistance,very good form stability,good ductility and excellent weldability. It is suitable for use at temperatures up to 1100°C.

Typical applications for Ualloy104B are used in olid hot plates,open coil heaters in HVAC systems,night-storage heaters,convection heaters,heavy duty rheostats and fan heaters. And also used for heating cables and rope heaters in defrosting and de-icing elements,electric blankets and pads, car seats,baseboard heaters,floor heaters and resistors.

Normal composition(%)

C	P	S	Mn	Si	Cr	Ni	Al	Fe	Other
Max									
0.08	0.02	0.015	1.00	1.0~2.0	18.0~21.0	30.0~34.0	-	Bal.	-

Typical Mechanical properties（1.0mm）

Yield strength	Tensile Strength	Elongation
Mpa	Mpa	%
340	675	35

Typical Physical properties

Density (g/cm^3)	7.9
Electrical resistivity at 20℃($\Omega mm^2/m$)	1.04
Conductivity coefficient at 20℃ (WmK)	13

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com

Information presentation property of Ualloy

Coefficient of thermal expansion	
Temperature	Coefficient of Thermal Expansion x10^{-6}/℃
20 ℃- 1000℃	19

Specific heat capacity	
Temperature	J/gK
20℃	0.50

Melting point (℃)	1390
Max continuous operating temperature in air (℃)	1100
Magnetic properties	non-magnetic

Temperature Factors Of Electrical Resistivity

20℃	100℃	200℃	300℃	400℃	500℃	600℃
1	1.023	1.052	1.079	1.103	1.125	1.141
700℃	800℃	900℃	1000℃	1100℃	1200℃	1300℃
1.158	1.173	1.187	1.201	1.214	1.226	-

Style of supply

Alloys Name	Type	Dimension	
Ualloy104BW	Wire	D= 0.03~8mm	
Ualloy104BR	Ribbon	W= 0.4~40mm	T= 0.03~2.9mm
Ualloy104BS	Strip	W= 8~250mm	T= 0.1~3.0
Ualloy104BF	Foil	W= 6~120mm	T= 0.003~0.1
Ualloy104BB	Bar	Dia= 8~100mm	L= 50~1000

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy