Ualloy 020
(Resistance heating wire and resistance wire)

Common Name: CuNi14,NC20

Ualloy020 is a copper-nickel alloy (Cu86Ni14 alloy) with low resistivity for use at temperatures up to 300°C.

Ualloy020 is kind of low resistance heating alloy.It is one of the key materials of the low-voltage electrical products. It is widely used in low-voltage circuit breaker, electric blankets.thermal overload relay, and other low-voltage electrical product.

Ualloy20 is typically used for low-temperature applications such as heating cables.

Normal composition(%)

Nickel	14	Manganese	0.3
Copper	Bal.		

Typical Mechanical properties（1.0mm）

Yield strength	Tensile Strength	Elongation
Mpa	Mpa	%
145	310	25

Typical Physical properties

Density (g/cm^3)	8.9
Electrical resistivity at 20℃($\Omega mm^2/m$)	0.2
Temperature factor of resistivity（20℃~600℃）$X10^{-5}$/℃	<38
Conductivity coefficient at 20℃ (WmK)	48
EMF vs Cu(μV/℃)(0~100℃)	-28

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy

Coefficient of thermal expansion	
Temperature	Coefficient of Thermal Expansion x10^{-6}/℃
20 ℃- 400℃	17.5

Specific heat capacity	
Temperature	J/gK
20℃	0.380

Melting point (℃)	1115
Max continuous operating temperature in air (℃)	300
Magnetic properties	non-magnetic

Corrosion resistance performance

Alloys	Working In atmosphere at 20℃	Working at max temperature 200℃				
		Air and oxygen contain gases	gases with Nitrogen	gases with sulfur oxidability	gases with sulfur reductibility	carburization
Ualloy020	good	general	general	general	bad	good

Style of supply

Alloys Name	Type	Dimension	
Ualloy020W	Wire	D= 0.06~8mm	
Ualloy020R	Ribbon	W= 0.4~40mm	T= 0.05~2.9mm
Ualloy020S	Strip	W= 8~200mm	T= 0.1~3.0
Ualloy020F	Foil	W= 6~120mm	T= 0.005~0.1
Ualloy020B	Bar	Dia= 8~100mm	L= 50~1000

TEL:+86-571-63255636 Email: sales@ualloy.com
FAX:+86-571-63256181 Web: www.ualloy.com
Information presentation property of Ualloy